



BURGOCOLOR



Grammatura	ISO 536	g/m <sup>2</sup>	80
Spessore	ISO 534	µm	102
Volume	ISO 534		1,28
Umidità assoluta	ISO 287	%	5
Ruvidità Bendsten	ISO 8791-2	%	280

Certificazioni: ECF - ISO 9706 - ACID FREE - HEAVY METAL ABSENCE CE 94/62 - FSC® MIX CREDIT SGSCH-COC-002122