



CAD ECO



Grammatura	ISO 536	g/m ²	60	80	90
Spessore	ISO 534	µm	78	102	117
Volume specifico	ISO 534	cm ³ /g	1,3	1,27	1,3
Ruvidità Bendsten	ISO 8791-2	ml/min	300	250	250
Bianco ISO	ISO 2470 (D65)	%	102	108	108
Opacità	ISO 2471	%	88	90	91

Certificazioni: 100% RICICLABILE - ECF