



## DIABLO BD



Grammatura	ISO 536	g/m <sup>2</sup>	80	90	100	120	140	170	190	250	300	350
Spessore	ISO 534	cm <sup>3</sup> /g	103	115	125	144	164	201	223	298	346	400
Opacità	ISO 2471	%	92	93	94	96	98	99	99	99	99	99
Bianco UV	ISO 2470	%	103,5	103,5	103,5	103,5	103,5	103,5	103,5	103,5	103,5	103,5
Bianco CIE	ISO 11475	%	145	145	145	145	145	145	145	145	145	145
Ruvidità Bendsten	ISO 8791-2	ml/min	225	225	225	225	225	225	225	225	225	225
Umidità ass.	ISO 287	%	6,2	6,2	6,2	6,2	6,2	6,2	6,2	6,2	6,2	6,2

Certificazioni: ECF - ISO 9706