



ESTRO gloss



Grammatura	ISO 536	g/m²	90	100	115	130	150	170	200	250	300	350
Spessore	ISO 534	µm	70	76	84	95	108	122	146	188	235	275
Volume specifico	ISO 534	cm ³ /g	0,78	0,76	0,73	0,73	0,72	0,72	0,73	0,75	0,78	0,78
Lucido Gardner	ISO 8254-1	%	71	73	77	78	78	78	78	78	75	75
Bianco CIE	ISO 11475	%	119	119	119	119	119	119	119	119	119	119
Bianco ISO	ISO 11475	%	94,5	94,5	94,5	95	95	95	95	95	95	95
Opacità	ISO 2471	%	91	93,5	95	96	97	97 min	98 min	98 min	98 min	98 min

Certificazioni: 100% RICICLABILE - ECF - FSC® SGSCH-COC-002122