



ESTRO Satin



Grammatura	ISO 536	g/m²	90	100	115	130	150	170	200	250	300	350
Spessore	ISO 534	µm	78	85	92	104	118	134	165	215	275	325
Volume specifico	ISO 534	cm ³ /g	0,86	0,85	0,8	0,8	0,79	0,79	0,83	0,86	0,9	0,93
Lucido Gardner	ISO 8254-1	%	45 max	45 max	45 max	45 max	45 max	45 max	45 max	45 max	45 max	45 max
Bianco CIE	ISO 11475	%	121	121	121	121	121	121	121	121	121	121
Bianco ISO	ISO 11475	%	97	97	97	97	97	97	97	97	97	97
Opacità	ISO 2471	%	92,5	94	95	96	97	98 min	98 min	98 min	98 min	98 min

Certificazioni: 100% RICICLABILE - ECF - FSC® SGSCH-COC-002122