



VINCIBRIGHT
FULLY COATED WHITE LINED CHIPBOARD
(WLC) WITH MANILLA BACK
GT 2

TECHNICAL SPECIFICATION

NOVEMBER 2023

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER 15° (*)		STIFFNESS L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m ²	µm	cm ³ /g	mNm	mNm	mNm	mNm
(270)	359	1.33	9.1	3.7	17.3	6.9
290	384	1.32	11.2	4.8	21.3	9.1
320	425	1.33	15.4	6.7	29.3	12.8
350	465	1.33	19.7	9.0	37.5	17.1
385	505	1.31	24.6	11.4	46.7	21.7
400	525	1.31	27.7	13.0	52.7	24.8
(425)	556	1.31	30.9	14.4	58.7	27.3
450	590	1.31	36.2	17.0	68.8	32.3
(480)	630	1.31	41.0	18.7	77.8	35.5
(500)	655	1.31	44.1	20.0	83.8	37.9
(550)	720	1.31	49.8	20.8	94.6	39.5

() NON STANDARD GRAMMAGE, AVAILABLE ON SPECIAL REQUEST ONLY.
 (*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS (AT PRODUCTION)		
TOP	82%	ISO 2470-2
BACK	55%	ISO 2470-2

TOLERANCES - SAMPLING ISO 186		
SUBSTANCE	+/- 2%	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
STIFFNESS	- 15%	for single determinations (95% of values)
BRIGHTNESS TOP/BACK	+/- 2	
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

