



JOKER GLOSS



Grammatura	ISO 536	g/m ²	90	100	115	130	150	170	200	250	300	350
Spessore	ISO 534	µm	70	80	92	101	125	143	178	235	290	342
Opacità	ISO 2471	%	92	93	95	97	98	98	98	99	99	99
Bianco UV ISO	ISO 2470	%	92	92	92	92	92	92	91	91	91	91
Bianco CIE	ISO 11475	%	120	120	120	120	120	120	120	120	120	120
Volume specifico	ISO 534	cm ³ /g	0,78	0,8	0,8	0,78	0,83	0,84	0,89	0,94	0,97	0,98
Lucido Gardner		%	75	75	75	75	75	75	72	72	70	70

Certificazioni: 100% RICICLABILE - ECF - FSC® MIX CREDIT SGSCH-COC-002122