



Grammatura	ISO 536	g/m²	60	70	80
Volume specifico	ISO 534	cm³/g	1,6	1,6	1,6
Opacità	ISO 2471	%	91	93	95
Spessore	ISO 534	μm	96	112	128
Bianco ISO	ISO 2470-2	%	73,5	73,5	73,5

Certificazioni: ECF - ISO 9706 - ACID FREE - HEAVY METAL ABSENCE CE 94/62 - FSC® MIX CREDIT SGSCH-COC-002122