


CAST GLOSS AP904 WK85 CERT. FSC® CERTIFIED

PRODUCT DESCRIPTION / BENEFITS

Face : Gloss white cast coated woodfree paper. FSC Certified.

Adhesive : Acrylic permanent adhesive. Good adhesion on a wide variety of materials including apolar substrates (like PE and PP).

Liner : One side siliconised clay coated Kraft. There may be slight variations in tone



TYPICAL USE

- Logistics & Mailing
- Promotional & Advertising

PRINTING & CONVERTING

Suitable for conventional printing methods (traditional offset and litho). Testing for suitability between media, printers and inks is always recommended prior to use.

PRODUCT RECOMMENDATIONS

General all-purpose paper, ideal for high quality labels.

SHELF LIFE

2 years in original closed packaging under storage conditions as defined by FINAT section 2.5 (20-25°C, 40-50% RH). Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life of the product.

CAST GLOSS AP904 WK85 CERT. FSC® CERTIFIED

PHYSICAL PROPERTIES / TYPICAL VALUES

FACE MATERIAL

CAST GLOSS FSC

Grammage	80 Gr/m2	ISO 536
Thickness	78 µm	ISO 534-80

ADHESIVE

AP904

Tack (N) Glass	11 N	FTM9
Min Labelling Temperature	0 °C	
Usage Temperature	-20/+70 °C	
Peel Value	10 N/25mm	FTM2

LINER

WK85

Grammage	82 Gr/m2	ISO 536
Thickness	85 µm	ISO 534-80

QUALITY CERTIFICATIONS & APPROVALS

- FSC License code: FSC-C106281

DISCLAIMER

Information on physico-chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change. All Fedrigoni products are sold subject to terms and conditions of sale. For more information, contact your Fedrigoni sales representative. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.