



SELENA IVORY.



Grammatura	ISO 536	g/m ²	80	90	100	120
Volume specifico	ISO 534	cm ³ /g	1,15	1,15	1,15	1,15
Opacità	ISO 2471	%	88	89,5	90,5	92
Bianco	ISO 2470	%	72	72	72	72
Ruvidità Bendsten	ISO 8791-2	ml/min	150	150	150	150
Umidità relativa	TAPPI 502-98	%	50	50	50	50

Certificazioni: ECF - ISO 9706 - ACID FREE - HEAVY METAL ABSENCE CE 94/62 - FSC® MIX CREDIT SGSCH-COC-002122